

PRODUCT ADVICE

WALL & CEILING PRIMER & UNDERCOAT



All Farrow & Ball paints are eco friendly and comply with the latest environmental legislation regarding the VOC (volatile organic compounds) content of paints.

Availability: In 750ml, 2.5 litre and 5 litre tins in ten colours (1, 10, 15, 18, 22, 26, 32, 37, 49 & White). Available direct from Farrow & Ball, our Showrooms and selected stockists internationally.

Usage: A water based primer and undercoat. Formulated for use on internal plaster walls and ceilings as a foundation for Farrow & Ball Estate[®] Emulsion and Farrow & Ball Modern Emulsion.

Preparation: Surfaces must be sound, clean, dry and free from dirt, grease and other contamination.

Plaster – For powdery surfaces, apply one coat of Farrow & Ball Stabilising Primer to bond unstable plaster, followed by one coat of Farrow & Ball Wall & Ceiling Primer & Undercoat.

PLEASE NOTE: British Standard 6150:2006 recommend a typical drying time for new plaster is 7 days for every 5mm thickness.

For highly absorbent bare substrates Farrow & Ball Wall & Ceiling Primer & Undercoat may be diluted with up to 50% water.

Suggested dilution rates:

	Brush	Roller
Bare dry skim plaster/sheet rock/lined walls	30%	30%
Bare dry plaster board	15%	15%
Patch filled	Up to 30%	Up to 30%

The dilution rate will depend on the porosity of the surface. A test patch is recommended to determine if further dilution is required.

Finish with a full undiluted coat to enhance the top coat colour.

When porous plasters are not sufficiently prepared, difficulties in application or variation in sheen and uneven colour may occur.

Pre-painted, non porous surfaces – apply one full coat of Farrow & Ball Wall & Ceiling Primer & Undercoat to promote adhesion and full colour depth.

Glossy or oil based surfaces – should be sanded down prior to cleaning with a detergent. Apply one full coat Farrow & Ball Wall & Ceiling Primer & Undercoat.

Painting: **Do not paint in temperatures below 10°C or excessive heat above 30°C.**

Stir thoroughly before use.

Clean up: Clean brushes and rollers with warm soapy water.

Cleaning: N/A

Disclaimer: The information given in these specification sheets and technical advice – whether verbal, in writing or by way of trials – is for guidance and is given in good faith but without warranty, since skill of application and site conditions are beyond our control. For further information please contact our Customer Services Department. We can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. This does not affect your statutory rights.



PAS_UK

PRODUCT ADVICE

WALL & CEILING PRIMER & UNDERCOAT



- Formulation:** Based on 100% acrylic resin.
- Storage:** This product is water based and must be protected from frost and extreme temperatures. Use within 6 months of purchase. We accept no responsibility for the deterioration of contents or packaging after this date.
- Disposal:** Though water based, please do not dispose of into watercourse. Waste materials must be disposed of in accordance with the Environmental Protection Act 1990 and relevant regulations made there under. For further information contact the environment office at your local council.
- Health & Safety:** Ensure good ventilation during application and drying. Avoid contact with skin and eyes. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. After contact with skin wash immediately with plenty of soap and water or a proprietary skin cleanser. Keep out of reach of children.

Safety Data Sheets are available for professional users on request.

- Environment:** **Actual VOC content g/l** 0.6 g/l
- VOC content w/w:** 0.04%
- Classification:** Minimal
- 2010 max. permitted limit grams per litre** 30 g/l
- CATEGORY** g

Coverage UNDILUTED	Drying Time	Recoat Time	Sheen Level	Thinners
Up to 65 m ² per 5 litres	1-2 hours surface dry.	4 hours dependant on conditions	N/A	Refer to Preparation section for guidance

Issue 3 - June 2010

Disclaimer: The information given in these specification sheets and technical advice - whether verbal, in writing or by way of trials - is for guidance and is given in good faith but without warranty, since skill of application and site conditions are beyond our control. For further information please contact our Customer Services Department. We can accept no liability for the performance of the products arising out of such use, beyond the value of the goods delivered by us. This does not affect your statutory rights.

PAS_UK