

# Little Greene

— PAINT & PAPER 1773 —

## INTELLIGENT MATT EMULSION

FORMERLY ULTIMATT EMULSION

### DESCRIPTION

A high quality, low odour, reinforced water based matt finish displaying excellent adhesion to existing aged alkyd finishes. Outstanding water resistance and excellent adhesion characteristics make this product highly suited for painting kitchen, bathroom and high traffic area walls. This product is suitable for both interior and exterior applications.

### PROPERTIES

Gloss Level	Matt (less than 5%)
Theoretical coverage	13 square meters per litre (varies with surface porosity & texture)
Recommended film thickness	30 microns dry, per coat.
Recommended number of coats	2
Surface dry	1 hours

Time to recoat	4 hours minimum
Volume solids	35%
Colour availability	All Little Greene colour ranges
Pack size availability	1, 2.5 & 5 Litre

\*The final sheen level may take up to seven days to be reached, depending upon film thickness and drying conditions.

### APPROVALS & STANDARDS

Manufactured under the auspices of ISO 9001:2008 quality & ISO 14001:2004 environmental management systems.

BS EN 71-3:1995 (BS 5665-3:1995) Safety of toys. Specification for migration of certain elements. (Test certificate available upon request)

2004/42/EC EU limit value for this product (cat.A/awb): 30 g/l (2010). This product contains max.2g/l VOC.

### SURFACE PREPARATION

**New wood:** For soft woods, knots should be sealed with knotting compound to prevent staining and then primed with Little Greene Traditional Oil Primer Undercoat or Little Greene Acrylic Primer Undercoat. Resinous hard woods require cleaning and treatment with Little Greene Aluminium Wood Primer (consult the relevant product data sheets for further details) prior to undercoating.

Ensure moisture content of the timber is below 15% before commencing application. Damp wood should never be painted as this may give rise to blistering, flaking, cracking and premature coating failure.

Green oak should not be painted unless it has been weathered for at least 6 months.

**Metals:** New ferrous metalwork should be hand, or mechanically cleaned, to remove any surface rust before application of Little Greene Traditional Oil Primer Undercoat. Non ferrous metals must be pre-treated or primed with an appropriate proprietary primer.

**Existing paint finish:** Remove all loose and flaking paintwork. Degrease with a suitable detergent solution, such as sugar soap. Rub down thoroughly with a medium grade sand paper to provide a key and a defect free smooth surface, "feathering in" areas where paint has been removed. Make good any repairs, sand and apply primer to exposed surface as appropriate.

Some existing vinyl silk and satin finish surfaces can be very water sensitive and soft, resulting in film cracking when overcoated. To ensure old existing coatings do not give this problem, it is advised to apply a small test area, which should be allowed to dry, and assessed, before full area application is commenced. In the event of the substrate showing cracking in this test, it should be sealed, before application of the emulsion paint, with a coat of oil based primer undercoat.

**Plastics:** For long term performance, clean & lightly sand down surfaces. Prime using a proprietary adhesion promoting plastics primer before applying the finishing coat.

**New plaster walls:** For plaster skim, allow at least four weeks for the plaster to thoroughly dry. Apply a primer coat by thinning the paint with a 5 to 25% (v/v) addition of clean water, depending upon the porosity of the substrate. Cut in by brushing at the same dilution recommendation as for priming, to promote flow and sealing of the substrate. Finish by applying two full coats.

For new, fully plastered walls, allow at least six months for the plaster to thoroughly dry before painting with Little Greene Intelligent Matt Emulsion.

This product is not recommended for painting lime or other natural plasters.

**Existing plaster walls:** Lightly wash any existing paint work to remove any dust or surface laitance. Apply a primer coat by thinning with a 0 to 25% (v/v) addition of clean water, depending upon the porosity of the substrate. Finish by applying at least one full coat, as required.

For significant colour scheme change, undercoating with Little Greene Acrylic Primer Undercoat is highly recommended.

This product is not recommended for painting previously painted lime or other natural plaster

Disclaimer - The information on this data sheet is correct to the best of our knowledge and experience. The Little Greene Paint Company reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, not does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.

The Little Greene Paint Company Limited, Wood Street, Openshaw, Manchester M11 2FB. England.

Tel: 0845 880 5855 (UK) Tel: +44 161 23 00 880 (Overseas) Fax: 0845 880 5877 (UK) Fax: +44 161 22 33 208 (Overseas)

mail@littlegreene.com www.littlegreene.com

# Little Greene

— PAINT & PAPER 1773 —

## INTELLIGENT MATT EMULSION

FORMERLY ULTIMATT EMULSION

### APPLICATION

Stir thoroughly before use. Do not apply to surfaces when the ambient temperature is below 5°C. Additionally, for external application, do not apply if there is a risk of rain or frost during the application or drying periods.

**Brushing:** Use a high quality synthetic bristle brush that is suitably sized for the project at hand. New brushes should be conditioned by washing in clean water and thoroughly drying with a clean, lint free, cloth.

Avoid immersing brush too far into the paint to prevent paint from entering the ferrule. Avoid drips and splashes by not overloading the brush. Apply paint in even strokes and only extend painting area such that a wet edge can be easily maintained. For the highest quality appearance, keep final brush strokes all in the same direction and never go over paint that has already begun to dry.

For intricate items, or where high ambient temperatures/high air flow conditions cannot be avoided, the open time maybe extended with a 10 to 15% (v/v) addition of a propriety water based paint conditioner. This advice is also applicable to large flat areas; however, use of a paint roller is the recommended application method in such cases.

Lightly rubbing down between coats will remove any dust motes and other surface contamination, producing a near professional finish.

**Roller:** Use a short nap wool blend type sleeve for best appearance on smooth surfaces. Increase nap length for textured surfaces, as appropriate, to ensure even and thorough coverage. Keep final strokes all in the same direction, maintaining a wet edge throughout. Never be tempted to go over already drying paint as this will lead to lap marking and flashing. When high ambient temperatures/high air flow conditions cannot be avoided, the open time maybe extended with a 10 to 15% (v/v) addition of propriety water based paint conditioner.

### Spray Finishing:

#### Conventional

Thin with up to: 40%(v/v) water  
Tip size: 1.60 to 2.00 mm (62 to 78 thou)  
Air pressure: 0.28 to 0.41 MPa (40 to 60 psi)

#### Airless

Thin with up to: 20%(v/v) water  
Tip size: 0.28 to 0.54 mm (11 to 21 thou)  
Pressure at tip: 12.6 to 19.6 MPa (1800 to 2800 psi)

### CLEANING

Remove excess paint and clean all equipment using clean water, immediately after use. Never store brushes or roller sleeves in water as this will result in deterioration of their application performance.

### STORAGE & SHELF LIFE

Store unused paint in a cool, dry, frost free area away from direct sunlight. Ensure tin lids are securely and correctly replaced after use. When unopened and stored under the conditions above, this product is stable for a minimum period of two years.

### AFTERCARE

**Cleaning:** For light surface soiling; use a dilute, lukewarm solution of domestic washing up liquid and a clean sponge or lint free cloth. Ensure sponge or cloth is well wetted (but not dripping), wash the affected area and repeat as required.

Ensure radiators are at room temperature before attempting to clean using the procedure above. Cleaning hot radiators may result in localised or uneven polishing of the surface.

To help prevent general build up, keep your home well ventilated during activities likely to contribute to oil and grease accumulation, like cooking. Tackle dust generated from DIY by, preferably, collecting at source or thorough vacuum cleaning.

To prevent marking, always use a soft brush attachment to vacuum clean adjacent surfaces.

**Special Care:** Avoid placing heavy objects onto surface for a least a week after painting.

**Repair:** Lightly rub down area to be repainted, apply suitable primer to any exposed substrate. Repaint item "break to break" with one or two coats as required. Spot repairs will almost always result in inferior aesthetic appearance.

### DISPOSAL & RECYCLING

Dispose of excess or waste paint via a licensed waste handing operator. Empty metal containers may be recycled (remove plastic handle on 2.5L and 5L tins).

### HEALTH & SAFETY

Always read the label on the can before use. Ensure maximum ventilation during application and drying. Consult product material safety data sheet for further details.

**Disclaimer** - The information on this data sheet is correct to the best of our knowledge and experience. The Little Greene Paint Company reserves the right to modify data contained herein, without notice. The information supplied does not absolve users from responsibility to carry out their own tests and experiments, not does it imply any legally binding assurance of certain properties or suitability for any specific purpose. Conditions of service and application may be beyond our control, so no liability whatsoever can be accepted on the basis of the information supplied herein.

The Little Greene Paint Company Limited, Wood Street, Openshaw, Manchester M11 2FB. England.

Tel: 0845 880 5855 (UK) Tel: +44 161 23 00 880 (Overseas) Fax: 0845 880 5877 (UK) Fax: +44 161 22 33 208 (Overseas)

mail@littlegreene.com www.littlegreene.com